



TECHNICAL DATA SHEET

EC-433

HIGH TEMPERATURE EPOXY CASTING SYSTEM ALUMINUM FILLED

DESCRIPTION

EC-433 aluminum filled epoxy casting systems are developed for use in heat resistant tooling applications such as prototype injection molding, vacuum forming, and other high temperature cast tooling applications. EC-433 offers 3 hardener options with various working times, suitable for any tool size. EC-433 is a room temperature hardening (B Stage) system, but a post cure is necessary for use over 150°F (66°C). Tools made with EC-433 can be used at continuous temperatures of 300°F (160°C) and intermittent temperatures up to 350°F (177°C). EC-433 features easy mixing, accepts higher loading of bulk aluminum, and exhibits greater dimensional stability.

APPLICATIONS

- Vacuum Form Molds
- Compression Molds
- Prototype Injection Moldings
- RIM Molds
- Foam Molds
- Other High Temp Cast Applications



PROPERTIES

TYPICAL HANDLING CHARACTERISTICS @ 77°F (25°C)

	EC-433-2 (FAST)	EC-433-3 (MEDIUM)	EC-433-4 (SLOW)
Mix Ratio (parts by weight)	100R/12H	100R/13H	100R/13H
Specific Gravity (g/cc)	1.62	1.59	1.59
Mixed Density (lbs/cu.in.)	0.058	0.058	0.058
Mixed Viscosity (cps)	9,000	15,000	15,000
Work Life	120 min.	200 min.	270 min
Demold Time	24 hours *** See Cure Schedule ***		
Complete Cure	Post cure	Post Cure	Post Cure
Maximum Casting Thickness (without aluminum filler additive)	< 1 inch	1 inch	<3 inches
Suggested Casting Mass (with N-20 Aluminum bulk filler additive)	< 2 cu/ft.	2-5 cu/ft.	> 5 cu/ft
Color	Gray Resin / Amber Hardener		
Shelf Life EC-433 Resin (in original unopened containers)	1 year	1 year	1 year
Shelf Life EC-433-2, 3 and 4 Hardeners (in original unopened containers)	2 years	2 years	2 years

NOTE: Bulk filler mix ratio is 100 parts-by-weight catalyzed EC-433 : 155 parts-by-weight N-20 Aluminum Grain

TYPICAL PHYSICAL PROPERTIES (Cast Bar 5" x ½" x ½")

	EC-433-2 (FAST)	EC-433-3 (MEDIUM)	EC-433-4 (SLOW)
Tensile Strength (ASTM D-638.91)	5,750psi (40MPa)	6,185psi (43MPa)	7,990psi (55MPa)
Tensile Modulus (ASTM D-638.91)	941,200psi (6,489MPa)	803,200psi (5,538MPa)	665,000psi (4,585MPa)
Flexural Strength (ASTM D-790.92)	10,620psi (73MPa)	10,280psi (71MPa)	11,670psi (81MPa)
Flexural Modulus (ASTM D-790.92)	700,900psi (4,833MPa)	620,300psi (4,277MPa)	756,000 psi (5,212MPa)
Compressive Strength (ASTM D-695.91)	16,300psi (112MPa)	16,100psi (111MPa)	18,650psi (129MPa)
Impact Strength – Notched Izod (ASTM D-256.93A)	11.8 in-lbf/in	7.22 in-lbf/in	8.8 in-lbf/in
Coefficient of Thermal Expansion (TMA) (ppm/°F (°C))	28 (51)	28 (51)	29 (53)
T _g by DMA	288°F (142°C)	305°F (152°C)	285°F (141°C)
Hardness	90 Shore D	90 Shore D	91 Shore D
Linear Shrinkage (200 cm ³ mold (-2); 4,650 cm ³ mold (-3 & -4))	0.005in/in	0.004 in/in	0.004in/in
Linear Shrinkage filled with N-20 aluminum grain (4,650 cm ³ mold)	0.002 in/in	0.003 in/in	0.003in/in

PROCESSING

RECOMMENDED CURE SCHEDULE

PRELIMINARY CURE:

24 hours @ 77°F (25°C) + 3 hours @ 150°F (66°C) is the minimum cure temperature

You may de-mold tool after the preliminary schedule is complete and the tool has cooled.

POST CURE SCHEDULE:

A conditioning post cure at a temperature equivalent to the constant operational temperature of your production mold is advised. If an additional post cure is necessary beyond the preliminary cure schedule, the recommended cure schedule is as follows:

- 2 hours @ 200°F (93°C)
- 2 hours @ 250°F (121°C)
- 2 hours @ 300°F (149°C)

Ensure proper heat curing temperatures are met by installing a thermocouple directly in the center of the tool.

Notes: It is always advisable to heat cure cast epoxy molds internally by using the copper tubing temperature control system built into your mold.

***If oven curing is your only option, it is advisable to complete the initial cure on the model at 125°F (52°C) for 8 hours or overnight before reverting to the higher post cure temperatures outlined above.

TECHNICAL DATA SHEET

EC-433

February 19, Version 01 /2021



DISTRIBUTED BY
Freeman Mfg. & Supply Co.
www.FreemanSupply.com

BUILDING TRUST



*****Extremely large cast molds should always be heat cured internally** and not moved or transported prior to completing an internal heat cure process of 150°F (66°C) minimum.

***Always allow a cast tool to cure 24hrs at room temperature before heat cure. This will prevent excessive exotherm and shrink stress from occurring.

***When taking cast tools through a preliminary or post cure phase always place tool in a room temperature oven and increase temperature at a rate of no more than 50°F (30°C) per hour.

***When cooling cast tools, always allow tool to remain in heat environment and decrease temperature at a rate of no more than 50°F (30°C) per hour. Do not remove tool from heat environment until center of tool has reached 100°F (38°C) or less. Removing tool at temperatures above 100°F (38°C) can result in thermal shock and warping.

Infused laminate - Carbon fiber, 3K plain weave, 8 layer, 0-90° rotation, 37% resin content

*1hr/50°C + 1hr/80°C + 2hr/120°C + 4hr/150°C cure **1hr/60°C + 1hr/80°C + 2hr/120°C + 4hr/180°C cure

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products:

- Ensure good ventilation.
- Wear gloves, glasses and protective clothes.

For further information, please consult the Safety Data Sheets.

STORAGE CONDITIONS

- This product has a shelf life of 12 months for the resin as indicated by the expiration date on the container when stored in original unopened containers between 47°F – 77°F (8°C – 25°C). The product shelf life for the hardener is 24 months between 60°F (15°C) and 77°F (25°C). Any opened can must be tightly closed.

PACKAGING

Packaging information on request, please contact your local sales representative or find your local contact on www.sikaadvancedresins.us

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

CONTACT

UNITED STATES

Sika Corporation

30800 Stephenson Highway
Madison Heights, Michigan 48071 – USA

Tel.: (+1) 248 588-2270

Fax: (+1) 248 577-0810

E-mail: advanced.resins@us.sika.com

Website: www.sikaadvancedresins.us