



Freeman Fre-Sil 76 Silicone Release Agent

Description

The Fre-Sil 76 Silicone Release Agent is a general-purpose, aerosol release agent compatible with a range of materials, including polyurethane, epoxy, silicone, and polyester. Easy to apply, fast drying, and capable of withstanding temperatures up to 500°F, the Fre-Sil 76 is well suited to a variety of molding applications.

Application Procedure

Shake Fre-Sil 76 well before use. Once mold surface is properly sealed, hold release ~ (12) in. from mold surface and apply a light, continuous coat. After applying initial coat, it is recommended to then use a soft brush to brush release across the entire mold surface to mitigate air entrapment. Apply second light coat and allow to stand for (5) minutes before putting mold into service.

The user shall determine the suitability of this product for their application and assumes all risks and liabilities associated with the use of this product. The exclusive remedy for all proven claims is replacement of our materials only and in no event shall Freeman Mfg. & Supply Co. be liable for special, incidental, or consequential claims.

READ SAFETY DATA SHEETS AND PRODUCT LABELS BEFORE USING PRODUCT