

# Technical Data Sheet

## Crystal Cast 1000



*Two Part Casting System  
Water Clear, UV Stable*

Crystal Cast 1000 is a two component thermoset system which is water clear when cured. Crystal Cast 1000 is ideal for rapid prototyping, embedding or any type of clear casting application.

### **Special Features**

- Optically clear
- UV stable
- Polishable to a high gloss
- Low viscosity
- Easily pigmented

### **Mix Ratio**

**Crystal Cast 1000A : Crystal Cast 1000B**  
By Weight 100 : 120

### **Product Data**

Property	Units	Crystal Cast 1000A	Crystal Cast 1000B	Mix
Appearance	-	Clear liquid	Clear liquid	Clear liquid
Viscosity (25°C)	mPa.s	300 – 500	100 – 150	100 – 350
Density (25°C)	g/cm <sup>3</sup>	1.25 – 1.30	1.08 – 1.13	1.16 – 1.21
Pot Life (200g, 25°C)	Minutes	-	-	8 – 10
Recommended Casting Thickness*	mm	-	-	2 – 10
Cure Time*	Hours	-	-	24

\*See "Curing" section.

# Technical Data Sheet

## Physical Properties

Properties	Standard	Units	Result (3hr 80°C Post Cure)
Hardness	BS EN ISO 868	Shore D	75 – 80
Linear Shrinkage*	500 x 50 x 5 mm	%	<0.4
Tensile Strength	BS EN ISO 527	MPa	60 – 64
Elongation at Break	BS EN ISO 527	%	4.5 – 5.5
Tensile Modulus	BS EN ISO 527	MPa	1500 – 1800
Flexural Strength	BS EN ISO 178	MPa	95 – 100
Flexural Modulus	BS EN ISO 178	MPa	2150 – 2450

\*See "Curing" section.

## Temperature Resistance

Cure Schedule	Standard	Units	Glass Transition Temperature (T <sub>g</sub> )
7 Day Room Temp.	DMA	°C	46 – 50
3 hours at 80°C	DMA	°C	58 – 62
16 hours at 100°C	DMA	°C	86 – 90

## Method of Use

The following instructions are to be considered as guidelines only, tests should be carried out to determine the most suitable processing conditions. Please contact Alchemie Ltd for more information on how to process this material.

## Mould Preparation

Before use ensure that the master model from which the mould is made has the exact finish that is required in the cast or finished units, i.e. for optimum clarity polish the master model to a very high sheen. Ensure that the mould is clean and dry. If the mould is made from metal or resin, use a release agent such as Release Agent R7. For flexible moulds we recommend ALCHEMIX RTV 240 addition cure silicone rubber. Condensation cured silicone rubber should not be used with Crystal Cast

# Technical Data Sheet

---

1000. It may be necessary to preheat the mould to 40°C in order to prevent shrinkage at the corners and sides of the casting.

## **Resin Preparation**

Open both A and B containers and examine for any signs of crystallization, place in the oven at 45 – 60°C if any crystals are observed. Ensure that both components are between 20 – 25°C before mixing. If using pigments, add the pigment to the part A. We suggest using 1 – 3% pigment. Tints can also be used to produce coloured parts that remain clear. Contact Alchemie's Technical Department for more information. Do not use water based pigments.

## ***Mixing instructions***

Mix the two components at the correct ratio, mixing carefully to avoid air inclusion and making sure that the material at the sides and at the bottom of the mix vessel is well stirred in to the middle. The material may become cloudy in appearance for a few minutes, continue mixing until the liquid becomes clear. Degas for approximately 5 minutes before pouring. Pour the material into the mould in one place to reduce air bubbles. Degas again if necessary, avoid boiling the material at very high vacuum.

## ***Curing***

The cure rate of Crystal Cast 1000 is affected by temperature, the product must be cast at temperatures greater than 20°C. Exact cure time will depend on the size and geometry of the casting and should be determined by customer testing. Thinner castings will take longer to cure than thicker castings, but generally, the product can be demoulded after 24 hours at 25°C. Incomplete cure can result in slight distortions or deformations of the components if forces are applied.

To optimise the cure, especially if the casting has thin sections, it is advisable either to use preheated moulds (see "Mould Preparation" above), or to post cure the castings after gelation. A typical post cure schedule would be to heat the material for 3 hours at 80°C. To achieve maximum thermal performance an extended post cure of 16 hours at 100°C is advised. To prevent any distortion during the post cure cycle, the unit should be placed on a conformer. When post-curing is complete, let the unit cool down slowly to room temperature, preferably in the oven. Sudden change in temperature can cause distortion or warping.

The recommended casting thicknesses stated above may not apply to small or large volume castings. Thicker castings will tend to shrink more than thinner castings due to the amount of heat generated. The cure rate of Crystal Cast 1000 is affected by temperature, the product must be cast at temperatures greater than 20°C.

# Technical Data Sheet

---

## ***Polishing tips***

Allow the casting to cure for at least 48 hours before machining or polishing. To avoid distortion ensure that the material does not reach temperatures above 50°C during machining or polishing. For general polishing of a moulded part use a fine liquid polish. If a deep scratch needs to be removed then wet and dry paper should be used in the following descending grit sizes 400, 800, 1000 and 1200. A course and then a fine polishing paste such should then be used finishing with a liquid polish. This information is for guidance only.

## **Storage**

Crystal Cast 1000A and B should be stored in original, unopened containers between 20 and 25°C. Crystal Cast 1000B may crystallise partially or completely if not stored at above 20°C. Like all polyurethanes, both components are moisture sensitive. Moisture absorption will cause excessive aeration in cast parts. KEEP THE PACKING TIGHTLY SEALED WHEN NOT IN USE.

If stored under the above conditions, Crystal Cast 1000A and B will have a shelf life of 6 months, from the date of production.

## **Packaging**

Crystal Cast 1000A is supplied in 835g and 4.175kg containers.  
Crystal Cast 1000B is supplied in 1kg and 5kg containers.  
(Please contact Alchemie Ltd for bulk supply)



# Technical Data Sheet

---

## **Further Information**

All data listed relates to typical values. This data should not be considered a product specification.

Our technical advice, whether verbal, or in writing is given in good faith, but without warranty – this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended process and use.

Before using any of our products, users should familiarise themselves with the relevant Technical and MSDS provided by Alchemie Ltd.

## **Alchemie Limited**

Alchemie Ltd develop, formulate and distribute Epoxy Resins, Polyurethane Resins, Silicones, Model Boards and Sheet Wax for use in the following applications:

- Electrical encapsulation
- Rapid Prototyping
- Prototypes
- Casting
- Gel Coating
- Laminating
- Model Making
- Master Models
- Flexible and rigid mould making

We offer fast service, technical support, development expertise, innovative products, diverse knowledge and experience.

We are a well-established company, with a high level of investment and experience. We implement BS EN ISO 9001.

**Alchemie® and Alchemix® are registered Trademarks of Alchemie Ltd, Warwick Road, Kineton, Warwick, England, CV35 0HU, England, United Kingdom. Ph: +44 (0)1926 641600; FAX: +44 (0)1926 641698**